

Sección útil de acero (cm²) según el número de cabillas

Designación	Diámetro mm	Peso kgf/m	Número de cabillas									
			Área (cm ²)									
			1	2	3	4	5	6	7	8	9	10
10M	10	0,617	0,78	1,57	2,35	3,14	3,92	4,71	5,50	6,28	7,06	7,85
12M	12	0,888	1,13	2,26	3,39	4,52	5,65	6,78	7,91	9,04	10,17	11,30
16M	16	1,577	2,01	4,02	6,03	8,04	10,05	12,07	14,08	16,09	18,10	20,11
20M	20	1,849	3,14	6,28	9,42	12,56	15,70	18,84	21,98	25,12	28,26	31,40
22M	22	2,985	3,80	7,60	11,40	15,20	19,00	22,81	26,61	30,41	34,21	38,01
25M	25	3,851	4,91	9,82	14,73	19,64	24,55	29,46	34,37	39,28	44,19	49,10

Designación	Diámetro plg cm	Peso kgf/m	Número de cabillas									
			Área (cm ²)									
			1	2	3	4	5	6	7	8	9	10
3	3/8" 0.953	0.559	0.71	1.43	2.14	2.85	3.57	4.28	4.99	5.70	6.42	7.13
4	1/2" 1.270	0.994	1.27	2.53	3.80	5.07	6.33	7.60	8.87	10.14	11.40	12.67
5	5/8" 1.588	1.554	1.98	3.96	5.94	7.92	9.90	11.89	13.87	15.85	17.83	19.81
6	3/4" 1.905	2.237	2.85	5.70	8.55	11.40	14.25	17.10	19.95	22.80	25.65	28.50
7	7/8" 2.222	3.044	3.88	7.76	11.63	15.51	19.39	23.27	27.15	31.02	34.90	38.78
8	1" 2.540	3.977	5.07	10.13	15.20	20.27	25.34	30.40	35.47	40.54	45.60	50.67
11	1 3/8" 3.581	7.906	10.07	20.14	30.22	40.29	50.36	60.43	70.50	80.58	90.65	100.72

Según las Normas COVENIN 316:2000, Fondonorma 316:2005 y 1753:2006, ACI 318-11